



STC382E - REV 1- 31.08.05

CERTIFICATION CATEGORY III

CE 0334

STANZOIL NK 22- 382

CE -Type Examination Certificate

0072/014/162/03/05/0027

issued by the approved body nr. 0072

I. T. F. H. – Av. Guy de Collongue - F- 69134 ECULLY CEDEX

Certificate of conformity of the quality Assurance System

issued by the approved body nr. 0334

ASQUAL - 14, rue des Reculettes - F - 75013 PARIS

This glove conforms to the provisions of Directive 89/686/EEC for protection against mechanical risks, contact heat, chemicals and micro-organisms.

STANZOIL NK 22 - 382

DESCRIPTION AND GENERAL PROPERTIES

Liquidproof glove made of **blue neoprene (polychloroprene)** over a **cotton knit lining**.

Do not contain natural rubber latex.

Curved fingers and contoured palm.

Non-slip finish in palm and fingers area.

Guaranteed **silicone-free**.

Conform to the FDA (American Food and Drug Administration) regulation for **food contact**.

Thickness of liquidproof material (in wrist area): **0.35 mm** (nominal value)

Glove thickness (in wrist area) : **0.9 mm** (nominal value)

Glove length (for all sizes) : **35.5 cm** (nominal value)

Sizes available : **7 - 7 ½**
8 - 8 ½
9 - 9 ½
10 - 10 ½
11 - 11 ½

Standard packaging :

- **12 pairs** in printed polyethylene bag
 - **72 pairs** per box

"CE"-TYPE EXAMINATION RESULTS



PROTECTION AGAINST CHEMICALS

According to EN 374 standard.
Liquidproof glove.

A C K L

Permeation data : see the enclosed chemical resistance chart.



PROTECTION AGAINST MICRO-ORGANISMS

According to EN 374 standard.

Acceptable Quality Level (**AQL**): **1.5%**



PROTECTION AGAINST MECHANICAL RISKS

Levels of performance according to EN 388 standard.

2 1 2 1

| | | |
| | | | ↳ **puncture resistance (0 to 4)**
| | ↳ **tear resistance (0 to 4)**
| ↳ **blade cut resistance (0 to 5)**
↳ **abrasion resistance (0 to 4)**



PROTECTION AGAINST HEAT

Levels of performance according to EN 407 Standard.

Only the mentioned test is relevant to the usage of the glove.

x 1 x x x x

↳ **contact heat (0 à 4)**

Thanks to its internal liner and its neoprene coating, this glove can be used for handling hot parts up to 100°C.

STANZOIL NK 22 – 382

SPECIFIC ADVANTAGES

- Two gloves in one for safer chemical protection.
- Excellent flexibility thanks to the unique MAPA process
- Raised pattern to provide optimum grip of wet parts.
- Comfort of the hand and thermal insulation thanks to the cotton lining.
- Good mechanical resistance.
- Recommended for persons sensitized to natural rubber proteins.
- Product manufactured in a MAPA factory which is ISO 9001 certified.

MAIN FIELDS OF USE

- Laboratory tests
- Mixing of chemicals
- Surface treatments
- Petrochemical refineries
- Handling valves
- Machinery maintenance
- Handling chemicals
- Engine assembly

INSTRUCTIONS FOR USE

For enhanced safety and service life of the gloves :

- Store the gloves in their packaging at a temperature above 5° C.
 - It is recommended to check that the gloves are suitable for the intended use, because the conditions of use at the workplace may differ from the "CE"-type tests.
 - It is not recommended for persons sensitized to dithiocarbamates and thiazoles to use these gloves.
 - Put the gloves on dry, clean hands.
 - Do not use the gloves in contact with a chemical for a duration in excess of the measured breakthrough time. Refer to the chemical resistance chart hereafter or contact the Technical Customer Service - MAPA PROFESSIONNEL in order to know this breakthrough time. Use 2 pairs alternatively when in long duration contact with a solvent.
 - Turn the cuff end down in order to prevent a hazardous chemical from dripping onto the arm.
 - Before taking off the gloves, clean them as appropriate :
 - in use with paints, pigments and inks: wipe with a clean cloth dampened with a suitable solvent, and rub over with a dry cloth
 - in use with a solvent (diluent, etc...): rub over with a dry cloth
 - in use with acids or alkalis: thoroughly rinse the gloves under running water, and rub over with a dry cloth.
- Caution :** using the gloves or submitting them to another cleaning or laundering process can alter their performance levels.
- Ensure the inside of the gloves is dry before putting them on again.
 - Inspect the gloves for cracks or snags before reusing them.

STANZOIL NK 22 - 382

GUIDE DE RESISTANCE CHIMIQUE

This glove is designed for protection against numerous chemicals such as acids, alcohols, petroleum, solvents. Avoid contacts with pure aromatic and chlorinated solvents. In order to know whether these gloves are appropriate for a given chemical, refer to the table hereafter or enquire to Mapa Professionnel's Technical Customer Service.

CHEMICAL	CAS Nr.	Chemical Resistance Index	Degradation Index (1 to 4)	Permeation (EN 374)	
				Breakthrough time (minutes)	Permeation Index (0 to 6))
Acetaldehyde*	75-07-0	=	4**	8	0
Acetic acid 50%*	64-19-7	++	4**	>480	6
Acetic acid (glacial)*	64-19-7	++	3**	288	5
Acetone	B 67-64-1	=	3**	6	0
Acetonitrile	C 75-05-8	=	NT	37	2
Acrylonitrile*	107-13-1	=	4**	16	1
Ammonium hydroxide 29 %	1336-21-6	++	4**	147	4
Aniline*	62-53-3	++	3**	102	3
Benzene*	71-43-2	-	1**	5	0
Butoxyethanol*	111-76-2	++	4**	295	5
Butyl acetate*	123-86-4	-	1**	11	1
Carbon disulfide*	E 75-15-0	-	4**	2	0
Carbon tetrachloride*	56-23-5	-	1**	12	1
1,2-Dichloroethane*	107-06-2	-	1**	6	0
Dichloromethane (methylene chloride)*	D 75-09-2	-	3**	2	0
Diethanolamine*	111-42-2	++	4**	>480	6
n-n Dimethylacetamide*	127-19-5	=	2**	26	1
Dimethylsulfoxide (DMSO)*	67-68-5	++	4**	346	5
Ethanol*	64-17-5	++	4**	363	5
2- Ethoxyethanol*	110-80-5	++	4**	265	5
Ethylacetate	I 141-78-6	-	NT	5	0
Ethylene glycol*	107-21-1	++	4**	>480	6
Formaldehyde 37%*	50-00-0	++	4**	>480	6
Hexane*	110-54-3	+	4**	34	2
n-Heptane	J 142-85-5	=	NT	28	1
Hydrazine 70%*	302-01-2	++	4**	>480	6
Hydrochloric acid 37%*	7647-01-0	++	4**	>480	6
Hydrogen fluoride (gaz) 99%*	7664-39-3	=	NT	71	3
Isobutanol*	78-83-1	++	4**	>480	6
Isopropanol*	67-63-0	++	4**	>480	6
Methanol	A 67-56-1	++	NT	133	4
Methyl ethyl ketone*	78-93-3	-	2**	8	0
Naphta VM & P*	8032-32-4	+	4**	25	1
Nitric acid 50%*	7697-37-2	++	4**	>480	6
Phosphoric acid 85%*	7664-38-2	++	4**	>480	6
Potassium hydroxide 50%*	1310-58-3	++	4**	>480	6
Pyridine*	110-86-1	-	2**	9	0
Sodium hydroxide 50%	K 1310-73-2	++	NT	> 480	6
Sulphuric acid 50%*	7664-93-9	++	4**	>480	6
Sulphuric acid 96%	L 7664-93-9	=	1**	46	2
Unleaded petrol*	8006-61-9	-	1**	10	0
Xylene*	1330-20-7	-	1**	7	0

NT : not tested yet * Tested according to ASTM F 739

** Degradation test based on weight change according to the modified ASTM D471 after a 60 minute contact

Chemical Resistance Index :

- ++ can be used for **long duration contact**
(limited to breakthrough time)
- + can be used for **short repeated contacts**
(for a total duration not exceeding the breakthrough time)
- = can be used against **splashes**
- **not recommended**

Degradation Index : a high index indicates a low degradation of the gloves in contact with the chemical.

Breakthrough Time : permeation test performed on the palm of the glove in MAPA laboratories, unless otherwise specified.

Permeation Index : a high index indicates a long breakthrough time.



"CE" DECLARATION OF CONFORMITY

The Company

MAPA s.n.c.

57, rue de Villiers
BP 190
92205 Neuilly-sur-Seine Cedex - France

declares that the following MAPA PROFESSIONNEL protective glove :

STANZOIL NK22 382

conforms to the glove which is the subject of "CE" certificate of conformity

nr 0072/014/162/03/05/0027

issued by the notified body nr **0072**

I.F.T.H

Av. Guy de Collongue - F-69134 ECULLY CEDEX

It is manufactured under a certified **Quality Assurance System** issued by the notified body nr **0334**

ASQUAL
14, rue des Reculettes
F-75013 PARIS

CERTIFICATION CATEGORY III

It conforms to the provisions of directive **89/686/CEE**, designed for protection against **chemicals, micro-organisms, mechanical risks and contact heat**, as specified in Article 8-4.(a) within the limits of use described in the technical documentation,

and is manufactured in conformance with the following **European Standards** :
EN 420, EN 374, EN 388 and EN 407.

Prepared at Neuilly-sur-Seine, on November 18th, 2005

MAPA
S.N.C. au Capital de 700.000 F.
57, rue de Villiers - BP 190
92205 NEUILLY S/ SEINE Cedex
Siège social : 2, rue Marzac, 75008 PARIS
R.C.S. PARIS B 814 397 720

M.RODOT
Technical Customer Service

MAPA S. N. C.
57, rue de Villiers - B.P. 190 - 92205 NEUILLY SUR SEINE CEDEX - FRANCE
Tel : 33 (0) 1 49 64 22 00 - Fax : 33 (0) 1 49 64 24 29
www.mapa-professionnel.com